



SANDWICHELEMENT

Top / Top Phon – Alu/SL

Product Information

Top / Top Phon – Alu/SL



Description:

Top sandwich elements consist of an extruded polystyrene core and top layers of aluminium and Stadurlon. The aluminium long side has a bevel of about 6 mm. Top Phon with 3.0 mm sound-absorbing inserts reduces the sound of rain on the roof by a multiple. The composite element is covered with a protective foil on both sides.

Properties:

- good sound insulation values
- UV-endurance
- optimum load-bearing capacity
- lightweight
- easy to process with the usual metalworking tools

Facings:

Inside: Stadurlon 1.3 mm | Outside: Smooth aluminium 0.72 mm. Surface coating: polyester paint.

Standard colours: RAL 9010 - white, RAL 7024 - Graphite grey matte, RAL 8004 - Copper brown, roussillon / rot patterned, zinc.

Core Material:

Extruded polystyrene foam, CFC-free or CO₂ foamed, low vapour permeability, lowest water absorbance, Fire protection class E according to EN 13501-1. The foam core is corrugated for optimum adhesion. No dust release during processing. Core material of different thermal conductivity λ D-value 0.029 - 0.035 is available. Stadur Top Phon with 3.0 mm sound-absorbing inserts reduces the sound of rain on the roof by a multiple.

Top Phon HP: heavy sound insulation insert of 700 kg/m³ | **Top Phon SW:** light sound insulation insert of 80 kg/m³

Formats:

Width: 1200 mm – Length: 3000 mm / 3500 mm / 4000 mm / 4500 mm / 5000 mm / 6000 mm / 7000 mm / 7500 mm

Other formats and fixed formats are available on request.

Overall Thickness	Type	U-Value (λ D 0.029)	U-Value (λ D 0.033)	R-Value (λ D 0.029)	R-Value (λ D 0.033)	Weight (kg/m ²)
16 mm	Top	1.53	1.68	0.49	0.43	4.40
32 mm	Top	0.83	0.92	1.04	0.91	4.92
52 mm	Top	0.53	0.59	1.73	1.52	5.58
32 mm	Top Phon HP	0.88	0.98	0.96	0.85	6.99
55 mm	Top Phon HP	0.52	0.58	1.75	1.55	7.75
65 mm	Top Phon HP	0.44	0.50	2.1	1.85	8.08
85 mm	Top Phon HP	0.34	0.38	2.79	2.45	8.74
32 mm	Top Phon SW	0.86	0.95	0.99	0.88	5.13
55 mm	Top Phon SW	0.51	0.57	1.79	1.58	5.89
65 mm	Top Phon SW	0.43	0.49	2.13	1.88	6.22
85 mm	Top Phon SW	0.33	0.38	2.82	2.49	6.88

Areas of Application:

Conservatory construction, shed roof glazing, overhanging roofs e.g. street cafés or carports, large advertising hoardings, porches for industrial buildings and shop passages

Note:

When laying Stadur Top, point loads (such as kneeling on it) should be avoided. For further information please refer to our brochure: Processing Instructions.

The product colours and surfaces shown in this brochure are subject to printing variations. Should you require exact colour and surface characteristics we recommend that you ask for a sample. Technical changes reserved. All business transactions are subject to our general terms and conditions which can be viewed at www.stadur.com.